

Supporting information

# Synthesis and Characterization of Anatase TiO<sub>2</sub> Nanorods: Insights from Nanorods' Formation and Self-Assembly

Syed Naveed Hosseini <sup>1</sup>, Xiaodan Chen <sup>1</sup>, Patrick J. Baesjou <sup>1\*</sup>, Arnout Imhof <sup>1\*</sup>, and Alfons van Blaaderen <sup>1\*</sup>

<sup>1</sup> Soft Condensed Matter, Debye Institute for Nanomaterials Science, Utrecht University, Princetonplein 1, Utrecht 3584 CC, The Netherlands; n.hosseini@uu.nl (S.N.H.); x.chen1@uu.nl (X.C.); p.j.baesjou@uu.nl (P.J.B.); a.imhof@uu.nl (A.I.); a.vanblaaderen@uu.nl (A.vB.)

\* Correspondence: p.j.baesjou@uu.nl (P.J.B.); a.imhof@uu.nl (A.I.); a.vanblaaderen@uu.nl (A.vB.)

**Table S1.** Calculated parameters used in Scherrer equation ( $L = K\lambda/\beta\cos\theta_{\beta}$ ) where ( $\beta \cong 0.041b$ ),  $L$  is the average size,  $\lambda$  is the X-ray wavelength,  $\beta$  is the full-width at half maximum value calculated in radians by fitting peaks with a 4-parameter Gaussian profile,  $b$  is a coefficient in the 4-parameter Gaussian fit profile,  $\theta_{\beta}$  is the Bragg angle for the measured peak, and  $K$  is a constant equal to 0.94.

plane index	$2T$	$T$	$\cos(T)$	$b$	$\beta$	$\beta\cos(T)$	$L$
{101}	29.8	14.9	0.966	1.117	0.0459	0.0443	3.78
{004}	44.6	22.3	0.925	0.221	0.0090	0.0084	19.97
{200}	56.6	28.3	0.881	1.324	0.0544	0.0479	3.506