Guiding the self-assembly of colloidal diamond 🐵

Cite as: J. Chem. Phys. **157**, 154503 (2022); https://doi.org/10.1063/5.0109377 Submitted: 12 July 2022 • Accepted: 09 September 2022 • Accepted Manuscript Online: 12 September 2022 • Published Online: 20 October 2022

🔟 Susana Marín-Aguilar, ២ Fabrizio Camerin and ២ Marjolein Dijkstra

COLLECTIONS

EP This paper was selected as an Editor's Pick



ARTICLES YOU MAY BE INTERESTED IN

The Asakura-Oosawa theory: Entropic forces in physics, biology, and soft matter The Journal of Chemical Physics **156**, 080401 (2022); https://doi.org/10.1063/5.0085965

Crystal nucleation of highly screened charged colloids The Journal of Chemical Physics **157**, 154905 (2022); https://doi.org/10.1063/5.0117867

Conductance of concentrated electrolytes: Multivalency and the Wien effect The Journal of Chemical Physics **157**, 154502 (2022); https://doi.org/10.1063/5.0111645





J. Chem. Phys. **157**, 154503 (2022); https://doi.org/10.1063/5.0109377 © 2022 Author(s).

Guiding the self-assembly of colloidal diamond

Cite as: J. Chem. Phys. **157**, 154503 (2022); doi: 10.1063/5.0109377 Submitted: 12 July 2022 • Accepted: 9 September 2022 • Published Online: 20 October 2022



Susana Marín-Aguilar, 🖲 🔟 Fabrizio Camerin, 🖻 🔟 and Marjolein Dijkstra 🖓 🔟

AFFILIATIONS

Soft Condensed Matter, Debye Institute for Nanomaterials Science, Utrecht University, Princetonplein 5, 3584 CC Utrecht, The Netherlands

^{a)}Author to whom correspondence should be addressed: s.marinaguilar@uu.nl ^{b)}Electronic mail: f.camerin@uu.nl ^{c)}Electronic mail: m.dijkstra@uu.nl

ABSTRACT

The assembly of colloidal cubic diamond is a challenging process since the shape and interaction parameters and the thermodynamic conditions where this structure is stable are elusive. The simultaneous use of shape-anisotropic particles and strong directional interactions has proven to be a successful path to exclusively nucleate this structure. Here, using molecular dynamics simulations, we explore in detail the conditions where the nucleation of cubic diamond from tetrahedral building blocks is favored. In particular, we focus on the effect of depletion and DNA-mediated interactions to form and stabilize this cubic diamond crystal. We find that a particular balance between the strength and the range of the depletion interactions enhances the self-assembly of stable cubic diamond, leading to a narrow region where this structure is nucleated. Moreover, we determine that stronger short-range depletion attractions may arrest the system, leading to the formation of percolating diamond networks or fully disordered gel structures. Accordingly, the internal arrangements of these structures exhibit a distinct variation in terms of fractal dimension and the presence of six-membered rings that increasingly acquire internal strain as the arrest gets more pronounced. With these results, we provide a clear route for the self-assembly of cubic colloidal diamond, toward the realization of crystals with superior photonic properties.

Published under an exclusive license by AIP Publishing. https://doi.org/10.1063/5.0109377

I. INTRODUCTION

The formation of colloidal crystals, intended as periodic arrays of colloidal particles, is made possible by the ability to synthesize and self-assemble these typical submicrometer-sized building blocks. In contrast to atomic units in macromolecules, the real potential of colloidal particles lies in the ability to precisely control both their shape^{1,2} and the way they interact,³ giving rise to structures and materials with a wide variety of properties and features.⁴ In this sense, a key role is played by the building blocks that can form the so-called open crystals which, compared to close-packed structures, find promising use in photonic crystals in which the transmission of visible light can be controlled.⁵⁻⁷ In this context, the cubic diamond structure is typically taken as the fundamental reference since it features a complete photonic bandgap at low dielectric constants.⁸ Its structure is characterized by the presence of particles with exactly four bonds in a tetrahedral arrangement. Moreover, these bonds are characterized for being in a staggered chair-like conformation so that the angle between two bonded particles is 109.5° , as shown in Fig. 1.9

oth their bling such structures.¹⁰ In fact, when four patches are tetrahedrally arranged, the basic units of the diamond conformation could be stabilized.¹¹⁻¹³ Although it is possible to assemble cubic diamond under certain conditions, often, other structures with a similar (free) energy but lacking a photonic bandgap are also obtained. Among these is the hexagonal diamond,^{13–15} which is characterized by three tetrahedral units in a staggered conformation and one in an eclipsed conformation, as illustrated in Fig. 1. Moreover, the size of the patch appears to play a crucial role. For instance, smaller patches are prone to stabilize complex clathrate arrangements.¹⁶ On the other hand, when patches are too wide, spontaneous crystallization could be hampered.¹³ Other recent approaches based on patchy particles rely on inverse designing the single units depending on the target structure that has to be assembled.^{17–21} In order to introduce

Being able to reproduce this type of structure is, therefore, of great significance, and over the years, several studies have been pro-

posed to understand how to adapt the colloidal particles in a way

that the self-assembly of the diamond crystal is promoted. Since

low-density crystalline phases are stabilized by anisotropic attrac-

tive interactions, patchy particles are ideal candidates for assem-



FIG. 1. Cubic (left) and hexagonal (middle) diamond structures. In the cubic diamond, the first four nearest neighbors are characterized by staggered conformations (bottom right), while in the hexagonal diamond, three nearest neighbors are characterized by a staggered conformation and one by an eclipsed arrangement (top right).

selectivity in the interactions and to exclude the formation of undesired patterns, a variable number of patches per particle are assigned a certain 'color' and species of different relative concentrations can be admitted to the self-assembly procedure. This type of approach based on the use of patchy particles could find experimental realization in the use of single-stranded DNA,^{22,23} which allows for high selectivity through a clever diversification of the nucleotide sequences.

Since closed ring patterns with an even number of components can be identified in crystalline diamond, the creation of building blocks that favor the formation of such motifs is another avenue to pursue.²⁴ Some recent studies lead in this direction. In particular, it has been shown that the use of a binary mixture of tetrahedral patchy particles allows for the sole formation of rings with an even number of units, thus avoiding rings with five or seven members that are typical of disordered structures.²⁵ The same idea is applied to a system of triblock patchy rods, where the extremities of the building blocks exhibit different interactions among each other. Finally, a promising route for obtaining colloidal diamond relies on polyhedrally shaped nanoparticles. In this sense, few attempts were based on truncated tetrahedral nanoparticles²⁸ and lately on modified gyrobifastigiums, whose shape consists of a complex eight-sided polyhedron.²⁹ For the latter method, an experimental counterpart still has to be designed.

These attempts and studies all point in the direction of devising a simple route to assemble crystalline diamond, given the potential that this structure holds. However, among other difficulties, it is challenging to exclusively favor the formation of cubic diamond and not other polymorphs, and the functionalization of colloids to obtain tetrahedral patchy particles is not immediate and easy to implement experimentally. An interesting idea involving the use of tetrahedral colloidal molecules has recently been presented by He *et al.*³⁰ The advantage of using these objects is that they can be built from very simple fundamental units and can, therefore, be provided with a very specific shape. Indeed, it was proposed to use colloidal fusion³¹ to form clusters of partially compressed spheres, where four monomers are at the vertices of a tetrahedron and one links them at the center; see Fig. 2. The latter remains exposed on the faces of the tetrahedron, and when covered with DNA, four triangular patches emerge. While the direct lattice of cubic diamond only exhibits a photonic bandgap for sufficiently compressed tetrahedral colloidal clusters, the inverse lattice, obtained by back-filling the interstices of the cubic diamond crystal with a high-index dielectric material and removing the tetrahedral colloidal molecules, presents a photonic bandgap that is less sensitive to the compression of the colloidal molecules.³⁰ We note, however, that the tetrahedral colloidal clusters employed to assemble cubic diamond in Ref. 30 only exhibit a photonic bandgap for the inverse lattice.

The successful assembly of cubic diamond based on such building blocks has to be attributed primarily to their shape, which also excludes the emergence of other types of lattices. In fact, thanks to the tetrahedral arrangement of the monomers, a steric interlocking mechanism takes place, allowing for the stabilization of staggered conformations between neighboring particles, as shown in Fig. 2. Energy minimization for this kind of conformation is further enhanced by DNA interactions acting among different units. In addition to this, the presence of DNA fragments and micelles in the experimental system also causes depletion interactions to take place between the colloidal molecules, inducing a further effective



FIG. 2. Building blocks for colloidal diamond. Each colloidal molecule is made of four spheres (or lobes) of diameter σ_A located at the vertices of a tetrahedron and of a central core particle of diameter σ_B . In the central row, we show three representative particles for varying core-to-lobe size ratios $s = \sigma_B/\sigma_A$. The DNA-coated central particle forms four disconnected patches for s = 1.18, while a more uniform coverage is found for s = 1.28, making the interaction less directional. In the bottom row, we show the (preferred) staggered and the (unfavored) eclipsed conformation for such tetrahedral colloidal molecules.

attraction. These interactions are far from being only collateral forces between colloidal particles but, on the contrary, they can be exploited for different purposes.³² Their short-range and controlled strength of attraction offers an ideal playground for studying the glass transition and gelation of dense colloidal suspensions. For colloidal particles, the addition of depletant agents has been demonstrated to be effective in inducing the assembly of crystalline phases.^{2,37,38} With respect to the tetrahedral clusters described above, the role of the depletion interactions is still not entirely clear, particularly in relation to the stronger attractions induced by the presence of DNA. It is expected that depletion promotes the interactions between particles and, thus, the formation of diamond, but to what extent this occurs remains to be defined. In principle, there might be conditions in which crystallization is greatly promoted and others in which the formation of ordered structures is hindered.

With the purpose of guiding the assembly of colloidal diamond and determining the most optimal conditions under which this occurs, we here perform extensive molecular dynamics simulations of tetrahedral colloidal molecules based on the experimental realization introduced above.³⁰ In particular, we explore the phase behavior of the system by changing a wide range of parameters that are significant for its further experimental investigation. We vary (i) the shape of the colloidal molecules determined by the core-to-lobe size ratio, (ii) the depletion concentration as characterized by the interaction strength, (iii) the depletion range set by the depletant-to-lobe size ratio, and (iv) the colloid density. In the first part of our investigation, we fix the colloid density to a low value in order to investigate the self-assembly at low concentrations. We observe nucleation of grains of cubic diamond at a relatively narrow range of depletion sizes and for weak depletion strengths. On the other hand, at large depletant concentrations, the induced attractions are strong enough to arrest the system, leading to percolating networks of cubic diamond or to completely random aggregates. Furthermore, in order to disentangle the contribution of DNA and to investigate its role in the crystallization of cubic diamond, we also consider the case in which the central core particle of the cluster is not coated with DNA, thus interacting solely via depletion interactions, similarly to the monomers. We then fix the core-to-lobe size ratio of the colloidal molecules and the depletant size, and explore the inner and global structural properties of the cubic diamond and the arrested phases in terms of nucleation paths, fractal dimensions, and the emerging patterns in the respective structures.

The remainder of this article is organized as follows. In Sec. II, we discuss the model and the effective potentials employed to mimic the DNA patchy and depletion interactions in simulations. In Sec. III, we first explore the effect of changing the size ratio between the core particles and the lobes located at the vertices of the tetrahedron in terms of the number fraction of particles with a diamond arrangement. We then perform simulations for colloidal molecules both with and without a DNA patchy interaction between the core particles. Subsequently, we move our attention to the structural properties of all the phases. Finally, we focus on a particular depletant size and explore the full kinetic phase diagram for varying colloid packing fractions. In Sec. IV, we summarize the main results and discuss our conclusions.

II. METHODS

A. Model and methodology

We base our model on the experimental realization by He *et al.*,³⁰ where anisotropic colloidal molecules with a tetrahedral shape and directional interactions were used. Such particles are formed by four colloidal spheres of diameter σ_A located at the vertices of a tetrahedron of side *a* and by a central spherical particle of diameter σ_B . We take σ_A as the unit of length in our simulations. The extent to which the central and the satellite spheres are allowed to overlap with each other is controlled both by their core-to-lobe size ratio $s = \sigma_B/\sigma_A$ and by the tetrahedron side length *a*. Schematic pictures displaying the structure of the colloidal particles at play are represented in Fig. 2. From the conformation of a single colloidal molecule, it is also clear how the interlocking mechanism between two tetrahedral colloidal clusters favors staggered conformations, with one lobe of a molecule interacting with two lobes of the second one. In this way, eclipsed arrangements are disfavored.

The colloidal tetrahedral particles as a whole interact via depletion interactions. To accurately account for such interactions, each lobe in the tetrahedron is assigned a combination of a purely repulsive Mie potential $U_{Mie}(r)$ and an Asakura–Oosawa depletion potential $U_{AO}(r)$,³⁹ which allows for a continuous treatment of the forces in molecular dynamics simulations. The total pair potential $U_{tot}(r)$ reads

$$U_{tot}(r) = U_{Mie}(r) + U_{AO}(r), \qquad (1)$$

with

$$\beta U_{Mie}(r) = \begin{cases} \frac{4\varepsilon}{k_B T} \left[\left(\frac{\sigma_A}{r} \right)^{96} - \left(\frac{\sigma_A}{r} \right)^{48} \right] + \frac{\varepsilon}{k_B T}, & r \le 2^{1/48} \sigma_A, \\ 0, & r > 2^{1/48} \sigma_A, \end{cases}$$
(2)

where ε is set to $1k_BT$ throughout this work, and with

$$\beta U_{AO}(r) = \begin{cases} -\eta_d^r \frac{(1+q)^3}{q^3} \left[1 - \frac{3r}{2\sigma_A(1+q)} + \left(\frac{r^3}{2\sigma_A^3(1+q)^3}\right) \right], & r \le \sigma_A + \sigma_d, \\ 0, & r > \sigma_A + \sigma_d, \end{cases}$$
(3)

where $q = \sigma_d/\sigma_A$ is the size ratio between the depletants of size σ_d and the colloidal lobe particles of diameter σ_A and η_d^r is the depletant reservoir packing fraction corresponding to a depletant activity z_d via $\eta_d^r = z_d \pi \sigma_d^3/6$. Finally, $\beta = 1/k_B T$ denotes the inverse temperature, with k_B being the Boltzmann constant. The parameters q and η_d^r control the characteristics of the potential, with q mainly modulating the range of the potential and η_d^r being its depth, as shown in Fig. 3.



FIG. 3. Total pair potential $U_{tot}(r) = U_{Mie}(r) + U_{AO}(r)$ for different depletant reservoir packing fractions η_d^r and the fixed depletant-to-lobe size ratio $q = \sigma_d/\sigma_A = 0.12$. The depletant reservoir packing fraction mainly controls the strength of the attractive interaction, while the depletant size controls the range of the potential.

In experiments, the central core monomer is coated with DNA, which induces a strong short-range attractive interaction via the exposed area of the particle. Such interactions were found to promote self-assembly. Here, we mimic this directional interaction $U_{DNA}(r)$ by allowing the central particles to interact through a 96–48 Mie potential in which $\varepsilon_{DNA} = 10 k_B T$,

$$\beta U_{DNA}(r) = \begin{cases} \frac{4\varepsilon_{DNA}}{k_B T} \left[\left(\frac{\sigma_B}{r} \right)^{96} - \left(\frac{\sigma_B}{r} \right)^{48} \right], & r \le r_{cut}, \\ 0, & r > r_{cut}. \end{cases}$$
(4)

Additionally, the potential is cut and shifted at $r_{cut} = 1.15\sigma_B$. As the presence of DNA suppresses depletion, the particles in the center interact only with a Mie potential.³⁰ To assess the effect of DNA in the colloidal diamond assembly, we also run simulations in which the central particles interact via depletion only. In all cases, the tetrahedral colloid is treated as a rigid body.

In order to explore the phase behavior of such colloidal molecules, we perform Langevin simulations in the NVT ensemble using LAMMPS (Large-scale Atomic), 40^{40} where N denotes the number of particles, V denotes the volume of the system, and T denotes the temperature. We simulate N = 1080 tetrahedral particles, and we fix the side of the tetrahedron $a = 0.7\sigma_A$, for which the inverse cubic diamond lattice exhibits approximately the widest photonic bandgap.³⁰ We start our simulations from three to four different random low-density configurations, which are slowly thermalized to $T^* = k_B T/\varepsilon = 1.0$ and progressively compressed to the desired final colloid density $\rho \sigma_A^3$, or packing fraction $\eta_c = \rho V_0$, with ρ being the number density and V_0 being the volume of a single colloidal molecule, determined by accounting for the overlaps of the constituting five spheres. This is followed by an equilibration run for at least $t = 1.0 \times 10^{\circ} \delta t$, where δt is the time step corresponding to $\delta t = 0.001\tau$, with $\tau = \sqrt{m\sigma^2/\varepsilon}$ being our time unit. Finally, a production run is made, with the system evolving for at least $2.5 \times 10^7 \delta t$. All simulations are performed in a cubic box with periodic boundary conditions.

B. Structural characterization

In order to follow the nucleation and crystallization of cubic diamond, we need a criterion to distinguish between diamond- and fluid-like particles. To this end, we first compute the correlation parameter $c_i(i,j)$ between the central particles of two neighboring colloidal molecules *i* and *j*,²⁶

$$c_{l}(i,j) = \frac{q_{l}(i) \cdot q_{l}^{*}(j)}{|q_{l}(i)||q_{l}(j)|}$$

=
$$\frac{\sum_{m=-l}^{l} q_{lm}(i) \cdot q_{lm}^{*}(j)}{\left(\sum_{m=-l}^{l} q_{lm}(i) \cdot q_{lm}^{*}(i)\right)^{1/2} \left(\sum_{m=-l}^{l} q_{lm}(j) \cdot q_{lm}^{*}(j)\right)^{1/2}},$$
(5)

where * indicates the complex conjugate and q_{lm} are the bondorientational order parameters introduced by Steinhardt *et al.*,⁴¹

$$q_{lm}(i) = \frac{1}{N_b(i)} \sum_{j}^{N_b(i)} Y_{lm}(\mathbf{r}_{ij}),$$
(6)

with $N_b(i)$ corresponding to the number of neighbors of particle *i* and $Y_{lm}(\mathbf{r}_{ij})$ being the spherical harmonics with total angular momentum *l* and its projection $-l \le m \le l$.

The correlation parameter $c_l(i,j)$ takes characteristic values depending on the local arrangement of neighboring molecules. In the case of cubic diamond, its intrinsic symmetry corresponds to a tetrahedral one, and hence, the expected number of neighbors per particle is four. Moreover, all the four bonds must have a staggered conformation. Here, we identify a staggered bond when $-1 < c_3(i, j) < -0.8$ ^{13,42} In order to have a clear classification of the particles that are in a cubic diamond environment, we first calculate the nearest neighbors of each tetrahedral particle through a Voronoi construction, we then identify the four nearest neighbors, and we finally calculate the corresponding $c_3(i, j)$. We remark that the four monomers at the vertices of each tetrahedral molecule *i* are not accounted for in the calculation of $c_3(i,j)$ as they only serve to favor the assembly in a staggered conformation. If particle *i* has four staggered bonds, it is considered part of a cubic diamond. We note that, when the cubic diamond nucleates into grain- or gellike structures, particles that belong to the interface between the crystal and the fluid phase tend not to fulfill this requirement. In order to include them, we also consider particles that have three staggered neighboring particles and at least one neighbor that is classified as a cubic diamond to be part of the crystalline diamond structure.

III. RESULTS AND DISCUSSION

A. The effect of both depletion and DNA interactions on the nucleation of cubic diamond

We start our discussion by exploring the effect of tuning the core-to-lobe size ratio $s = \sigma_B/\sigma_A$ and the depletion interaction on the nucleation of cubic colloidal diamond. In particular, we focus on the effect of depletant-to-lobe size ratio $q = \sigma_d/\sigma_A$ and the depletant reservoir packing fraction η_d^r . We run *NVT* simulations at fixed colloid number density $\rho \sigma_A^3 = 0.06$, varying $s \in \{1.18, 1.22, 1.24, 1.28\}$, $q \in \{0.08, 0.25, 0.40\}$, and $\eta_d^r \in [0.05, 0.40]$. Relative to the original experimental system,³⁰ the values of the core-to-lobe size ratio

s fall within the ones analyzed experimentally. For the depletantto-lobe size ratio q, we consider a much wider range, including the experimental one, that is around $q \approx 0.1$.

For each simulation at different conditions, we compute the number fraction of particles in a cubic diamond environment N_D/N , as described in Sec. II B. In Figs. 4(a)-4(c), we show N_D/N for DNA-functionalized colloidal molecules as a function of η_d^r for selected values of depletant-to-lobe size ratios q and core-to-lobe size ratios s. For each q, we also report on the upper axes the corresponding interaction strength βU . Here, we take the interaction strength $\beta U = |\beta U_{min}(r)|$, with $\beta U_{min}(r)$ corresponding to the minimum of the total pair potential in Eq. (1) (see Fig. 3). For the present system, where particles interact via soft interaction potentials, this appears to provide a more reasonable estimate than the contact energy as reported, for instance, in Ref. 43. In general terms, we first note that, by increasing q, the range of η_d^r in which diamondlike structures are found progressively widens. This effect is given both by the amount of diamond that is found for each s and by the fact that at high q, large fractions of staggered arrangements are found for increasing values of depletant concentrations η_d^r . Overall, while for q = 0.08 cubic diamond arrangements are mainly found for $0.05 < \eta_d^r < 0.25$, for q = 0.40 they are found for almost the entire η_d^r range explored from 0.05 to 0.40. Therefore, an increase in the range of the potential, provided by larger q, effectively favors the assembly in staggered conformations at all depletant concentrations.

Despite this, not all the sizes of the central core contribute equally to the formation of these type of structures, suggesting that a fine-tuning in the value of the core-to-lobe size ratio s is actually crucial. In particular, we observe high fractions of particles arranged in a staggered conformation for very specific s, namely, s = 1.22 and 1.24. In these cases, at appropriate conditions, even more than 80% of the particles adopt a cubic diamond conformation. On the contrary, for a small size of the central core, less particles are found in diamond conformations, as reflected by smaller values of N_D/N and with the emergence of random structures. This is particularly evident for depletant-to-lobe size ratios $q \gtrsim 0.25$. This behavior can be explained by observing the structure of the particle as the size of the central core is varied, as depicted in Fig. 2. In fact, for small s, the directionality of DNA interactions is enhanced by the presence of four well separated triangular patches in between the lobes of the colloidal molecules. This implies that the nucleation of cubic diamond structures is achieved only for narrow η_d^r ranges. On the other hand, when the size of the core particles is too large, the DNA interactions acquire a stronger isotropic character, which is reflected in the loss of ordered staggered arrangements between colloidal molecules. This can be observed for the s = 1.28 tetrahedral colloidal clusters, for which the range of η_d^r where N_D/N is non-zero is always smaller



FIG. 4. Number fraction of particles N_D/N identified as a cubic diamond as a function of depletant reservoir packing fraction η'_d (lower axis) or interaction strength βU (upper axis) for a system consisting of tetrahedral colloidal molecules, whose central core interaction (a)–(c) mimics the presence of DNA functionalization or (d)–(f) presents solely depletion interactions, at colloid number density $\rho\sigma_A^3 = 0.06$. Data are shown for different depletant-to-lobe size ratios $q = \sigma_d/\sigma_A = 0.08, 0.25$, and 0.40 (from left to right) and for core-to-lobe size ratios $s = \sigma_B/\sigma_A = 1.18, 1.22, 1.24$, and 1.28 as labeled.

than the other two intermediate core-to-lobe size ratios *s* analyzed. In the latter case, the highest number of diamond arrangements is found for the lowest η_d^r compared to the other size ratios, indicating that the nucleation is led by the strong DNA-mediated attractive interaction, and hence, for large *s*, a smaller depletion attraction is required to achieve an ordered structure. We remind that all calculations represented in Fig. 4 are performed for the same size of the tetrahedron side $a = 0.7\sigma_A$. By changing this parameter, we simply expect a shift in the values of q, η_d^r and *s*, although the observed phenomenology would be the same.

B. The effect of solely depletion interactions on the nucleation of cubic diamond

This picture highlights the non-trivial interplay between the interactions at stake: only for specific combinations of the parameters, high yields of cubic diamond can be obtained. To deepen our understanding on the role played by the DNA in the formation of cubic diamond structures, we analyze simulation runs for the same set of parameters but now for colloidal molecules whose core particles only present attractive depletion interactions as for the monomers in the lobes. The number fraction of colloidal diamond N_D/N found for such systems is reported in Figs. 4(d)-4(f). By comparing with the previously described case, the overall amount of particles in a cubic diamond arrangement globally reduces and basically zeroes for q = 0.4. However, for q = 0.25, high fractions are still found for a wide range of η_d^r and for a smaller range for q = 0.08. The fact that under such conditions we still find particles arranged as colloidal diamond demonstrates that the shape of the particles in the presence of an attraction such as that given by the depletants suffices to create staggered conformations. Experimentally, this would certainly constitute an advantage since often the DNA functionalization may not be effective, besides typically involving a highly elaborated procedure. Avoiding the use of DNA would also allow for a more precise control on the depletant concentration for the absence of dispersed fragments in the solution. On the other hand, based on our evidence, it appears that the presence of DNA on the core particles gives a substantial contribution to generate colloidal diamond conformations with high yields and for a wide parameter space.

C. Kinetic phase diagram as a function of depletant size and interaction strength

In the case of colloidal particles that interact via short-ranged attractive interactions, percolating gel networks can be formed due to the arrest of a gas–liquid phase separation that is metastable with respect to a broad gas–solid transition.^{43–45} This non-equilibrium phenomenon of gelation has been studied in detail for a mixture of colloidal spheres and non-adsorbing polymer in both simulations and experiments.^{43–45} The arrest of this spinodal network is either due to crystallization at sufficiently low interaction strength βU or caused by an attractive glass transition that meets the liquid binodal at high βU .^{43–45}

In our case, the use of large values of η_d^r induces strong shortrange attractive depletion interactions, and hence, we may also expect under certain conditions the formation of not only compact crystal grains of cubic diamond but also more branched and open structures, with the latter possibly retaining a certain degree of crystalline order. We therefore characterize in detail the structures that are formed for all the explored values of q and η_d^r . Here and in the following, we focus on the assembly of colloidal molecules whose core particles are functionalized with DNA.

To investigate whether or not gelation occurs in our system of tetrahedral colloidal molecules, we first check under which conditions the system percolates. To this end, we first obtain the largest cluster formed by the colloidal molecules and check whether it spans the dimensions of the simulation box. Here, we consider two colloidal molecules to belong to the same cluster when the distance between their centers is less than a typical cut-off radius $|\mathbf{r}_i - \mathbf{r}_i| < r_c$, where we choose $r_c \approx 1.6\sigma_A$, which allows for a correct identification of the percolating cluster. After having identified the extension of the largest cluster in each direction l_i , with i = x, y, z, we determine a system to be in a gel-like percolating network if $l_i > L - 2\sigma_B$, where L is the size of the box in one direction. We note that even if the system forms a gel-like percolating network, the amount of crystalline structures is still considerable. We classify a system as a diamondgel-like percolating network when the system percolates and the fraction of particles labeled as diamond is $N_D/N \ge 0.25$, while for a simple gel, the latter condition is not required. Finally, a system is considered as cubic diamond when $N_D/N \ge 0.25$, and it forms a non-percolating compact crystal grain.

Our results are summarized in Fig. 5 in a kinetic phase diagram for a system consisting of DNA-functionalized tetrahedral colloidal molecules at a colloid number density $\rho \sigma_A^3 = 0.06$ as a function of the depletant-to-lobe size ratio $q = \sigma_d / \sigma_A$ and interaction strength βU for various core-to-lobe size ratios $s = \sigma_B / \sigma_A$. For all core-to-lobe size ratios s and depletant sizes q, the system typically remains in a fluid phase at small interaction strengths βU , thus not nucleating any crystal phase. For sufficiently small size ratios s, e.g., s = 1.18, the phase diagram is dominated by an isotropic fluid phase, and the fluid region can be found for a wide range of interaction strengths βU and depletant size ratios q, which is consistent with the small values of N_D/N found for $\beta U \lesssim 2$ in Fig. 4. A typical configuration of the fluid of tetrahedral colloidal molecules is reported in Fig. 6(a). Upon increasing βU , the fluid is followed by the nucleation of cubic diamond. The set of parameters where nucleation occurs into a well-defined diamond crystal grain without percolation is relatively narrow, corresponding to an interaction strength $0.5 \le \beta U \le 2.5$ depending on *s*. In general, at larger interaction ranges, that is for larger depletant sizes q, the concentration of depletants needed for nucleating the cubic diamond is lower as less cohesive energy is needed to form four staggered bonds per particle. This is in contrast to smaller values of q, for which slightly stronger interactions are needed to find good nucleation. As a consequence of the intrinsic tetrahedral shape of the colloidal molecules, we frequently find the formation of crystal grains with an octahedral shape, as reported in Fig. 6(b). For the case where all monomers interact via depletion only, the region where diamond grains are nucleated is further restricted (see Fig. S1), supporting the role of DNA to enhance crystallization.

Close to the region in the kinetic phase diagrams of Fig. 5 where non-percolating cubic diamond is formed, we observe the formation of a percolating network at slightly higher interaction strengths βU . This phenomenon has been previously observed for other systems presenting short-ranged attractive interactions and typically signals the presence of a metastable gas–liquid phase transition.^{43,46}



FIG. 5. Kinetic phase diagram of a system of DNA-functionalized tetrahedral colloidal molecules at a colloid number density $\rho\sigma_A^3 = 0.06$ as a function of depletant size $q = \sigma_d/\sigma_A$ and interaction strength βU for varying core-to-lobe size ratios $s = \sigma_B/\sigma_A$: (a) 1.18, (b) 1.22, (c) 1.24, and (d) 1.28. Four different phases are identified, namely, cubic diamond crystals (dark blue diamonds), percolating cubic diamond gel-like structures (pink to purple shaded circles), disordered percolating gel networks (blue triangles), and an isotropic fluid phase (light blue pentagons). Different shades of pink denote different number fractions of cubic diamond N_D/N in the percolating structures following the color bar. The gray dashed line in (c) identifies the parameters for which we carry out the structural analysis in Figs. 6–8.

An interesting aspect concerns the fact that the structure of the percolating network we find in this region is not disordered. On the contrary, most of the particles have neighbors in a staggered conformation, effectively stabilizing a cubic diamond crystal in a mesoscopic gel-like structure, as shown in Fig. 6(c). This type of structure is found for a wide range of interaction strengths βU for s = 1.22 and 1.24 and effectively constitutes the most dominant phase for these two size ratios s. This scenario is consistent with what is depicted in Fig. 4, where we indeed found that for these size ratios, N_D/N is overall larger compared to that of colloidal molecules with a different s. Nonetheless, this emphasizes how finding a high N_D/N is not always a sufficient condition for having a structure in a crystalline compact grain. On the opposite side, moving to s = 1.28, an apparent lower fraction of particles in the diamond environment (see Fig. 4) results in a sharp decrease in the diamond-gel phase in favor of the presence of crystalline diamond in a slightly wider range than that found for lower *s*.

Directionality of the central core particle also plays a crucial role in the formation of staggered structures. In fact, the moment this aspect is lacking, as in the case of the two size ratio limits, fully disordered conformations prevails (see Fig. 5). In all cases, as the interaction strength gets stronger, the arrest is more pronounced and the crystallinity is gradually lost, leading to a fully disordered gel network, as the one shown in Fig. 6(d). In case the central particle is not coated with DNA, the interaction range at which disordered phases are found is lower compared to the case discussed here and starts already at $\beta U \approx 2$ (see Fig. S1).

To summarize, the assembly of tetrahedral colloidal molecules into cubic diamond requires a precise choice in terms of interaction strengths and, hence, in the concentration of solutes acting as depletants. When deviating from these values, arrested phases are found, at first maintaining an intrinsic crystalline structure before forming disordered phases at higher interaction strengths. A less stringent requirement seems to emerge, instead, in terms of the depletant size q, provided that the core-to-lobe size ratio sis chosen appropriately. We note that we find no other crystalline structures for the parameters and ranges that we explored in our simulations.

D. Structural features of the different phases

In Sec. III C, we observed how the kinetic phase diagrams display both crystalline diamond structures and arrested states as a result of the strong interactions caused by the depletant agents. We now explore in detail such phases by analyzing their peculiarities and the differences in their local structure.

The crossover from the region where diamond grains are nucleated to the region in which percolating systems are formed is narrow and strongly depends on the precise value of the depletant size q and depletant reservoir packing fraction η_d^r . In order to shed light on the mechanism of nucleation of cubic diamond and the difference between percolating and non-percolating structures, we focus on a set of parameters s and q for which we find all the phases we are interested in and we characterize the structural evolution of the system. In particular, we analyze the selected values of η_d^r , corresponding to different βU , for a system with s = 1.24 and q = 0.12, for a fixed density of the colloidal molecules $\rho \sigma_A^3 = 0.06$, spanning the cases evidenced by the gray dashed line in Fig. 5(c).



FIG. 6. Typical configurations obtained from simulations for the phases found for the tetrahedral colloidal molecules at a colloid number density $\rho \sigma_A^3 = 0.06$ for a core-to-lobe size ratio $s = \sigma_B/\sigma_A = 1.24$ and depletant-to-lobe size ratio $q = \sigma_d/\sigma_A = 0.12$ [gray dashed line in Fig. 5(c)]: (a) isotropic fluid phase, (b) crystal grain of cubic diamond with an octahedral shape, (c) percolating cubic diamondgel-like structure, and (d) a disordered percolating gel network. Top panels report the full colloidal molecules, while bottom panels display only the core particles.

We inspect the number fraction of particles identified as cubic diamond N_D/N and the number of clusters \mathcal{N}_{DC} formed by colloidal molecules in a cubic diamond environment as a function of simulation time t/τ and report the results in Figs. 7(a) and 7(b), respectively. Simulation snapshots and videos for the nucleation process are, instead, reported in Fig. S2 and Videos S1–S5. For \mathcal{N}_{DC} , we consider only clusters consisting of more than ten molecules. A different choice of this threshold does not qualitatively affect the results. It is immediately evident that we can identify three different regimes: low, intermediate, and high βU . Nucleation of cubic diamond grains corresponds to the first regime, where the fraction of colloidal molecules in a staggered conformation slowly increases after a short waiting time. This process, which characterizes the nucleation and growth of a single cubic diamond cluster, allows the particles to slowly rearrange by progressively forming a well-ordered compact structure (Fig. S2 and Video S1). As the interaction strength βU increases, the growth in N_D/N is increasingly pronounced and reaches a plateau at shorter times. In this regime, the interactions are such that locally an ordered crystal can still be obtained, while being nucleated into a branched gel-like structure. For this reason, we observe a large number of diamond clusters \mathcal{N}_{DC} at short times which, depending on the degree of arrest of the system, either merge into a single elongated structure or remain separated by disordered regions (Fig. S2 and Videos S2-S4). The concurrent presence of disordered arrangements is consistent with an overall lower fraction of diamond at long times. At even higher depletant concentrations, for $\beta U \gtrsim 4$, the system is immediately arrested in a disordered conformation and no diamond-like structure is nucleated over time (Fig. S2 and Video S5).

As expected, this picture is consistent with the representation given by the local bond order parameter for cubic diamond. In particular, in Fig. 7(b), we plot the average correlation parameter $\langle c_3(i,j) \rangle$ as a function of time, where the average is performed over $N_b = 4$ neighbors. For increasing interaction strengths, $\langle c_3(i,j) \rangle$ tends to values closer to zero, reflecting the fact that fewer and fewer particles are in a cubic environment, as $c_3(i,j)$ progressively deviates from -1. However, it is important to note that the mean value of the correlation function, as calculated here, is also affected by the presence of particles at the interface. As a result, $\langle c_3(i,j) \rangle$ also shifts toward values closer to zero due to a lower number of first neighbors in a staggered conformation. To understand whether the increase is only due to a loss of crystalline environment and the role played by the interface, we calculate for each state point the surface area of the structure being formed over time by means of a surface mesh⁴⁷ that encompasses the largest cluster. As can be observed in Fig. 7(c), the formation of a crystalline grain is associated with a smaller surface area, given that the colloidal molecules are arranged in a more compact structure. For larger interaction strengths, greater and comparable surface areas are retrieved, consistent with the presence of more expanded structures. Thus, except for the lowest interaction strength where the compact diamond crystals are stabilized, the increase in the value of the correlation parameter $\langle c_3(i,j) \rangle$ for $\beta U \gtrsim 1.5$ can essentially be attributed to a progressive loss of crystallinity in the structure rather than to a larger amount of particles at the surface.

The nucleation and formation of crystalline and arrested phases are often characterized by the emergence of characteristic local structures.^{48–50} For instance, the formation of ring motifs between



FIG. 7. (a) Number fraction of particles N_D/N identified as cubic diamond, (b) number of clusters consisting of particles in a cubic diamond environment \mathcal{N}_{DC} , (c) average correlation parameter $\langle c_3(i,j) \rangle$, and (d) surface area A/σ_A^2 of the assembled structures calculated by means of a surface mesh as a function of simulation time t/τ for a system of DNA-functionalized tetrahedral colloidal molecules with a core-to-lobe size ratio s = 1.24 and depletant-to-lobe size ratio q = 0.12 at colloid density $\rho \sigma_A^3 = 0.06$ for varying interaction strengths βU as labeled [gray dashed line in Fig. 5(c)].

neighboring particles was identified in the nucleation pathways of patchy particles into open crystal structures.^{26,27} In particular, for cubic diamond and its polymorphs, the inner structure presents rings consisting of six or eight members.²⁶ Here, we explore how the formation of such structures occurs in our systems of anisotropic

tetrahedral colloidal clusters. In particular, we exclusively focus on six-membered rings formed by the central monomers of the tetrahedral colloidal molecules, which are known to retain a chair-like or staggered conformation in perfect diamond crystals. To this end, we first identify the nearest neighbors through a cutoff distance $r_c = 1.6\sigma_A$, corresponding to the first minimum of the radial distribution function of a cubic diamond formed by our model, ensuring that at most four nearest neighbors are taken into account. We verified that a variation of r_c in between the first and second peak of the radial distribution function does not affect the correct identification of the neighbors and, thus, of the rings (not shown). A six-membered ring is identified when, starting from a given particle, it is possible to return to the same one, passing through five other particles that are consecutive first neighbors to each other. To shed light on the difference between the structures found at different depletion strengths, we compute the fraction of particles belonging to a six-membered ring $N_{\nu=6}/N$ as a function of time. In Fig. 8(a), we show $N_{\nu=6}/N$ for different interaction strengths βU . For low and intermediate interaction strengths, corresponding to low and intermediate depletant concentrations, the curves closely resemble the trends of N_D/N shown in Fig. 7(a). A progressive growth in $N_{\nu=6}/N$ is, indeed, found for the set of parameters that leads to crystalline grains, while systems that are percolating display a quick saturation at short times. For the highest interaction strength, instead, the number of six-membered rings is always non-zero and essentially constant over time. Since this type of ring occurs in all phases, it is therefore reasonable to expect their internal conformations to be very dissimilar. In particular, the internal angle found between particles in a perfect chair-like conformation amounts to $\theta_{ijk} = 109.5^{\circ}$.⁹ If the internal angle θ_{ijk} deviates from this value, the system acquires a so-called angular strain $\xi = \theta_{ijk} - 109.5^{\circ}.^{51}$ We report in Fig. 8(b) the angular strain probability distributions per particle for a crystalline cubic diamond (s = 1.24, q = 0.12, and $\eta_d^r = 0.12$) and for a disordered gel (*s* = 1.24, *q* = 0.12, and $\eta_d^r = 0.40$). Other probability distributions for intermediate βU are reported in Fig. S3. As expected, the angular strain for diamond structures is distributed around zero, with most of the particles in the crystal grain retaining six-membered rings in a chair-like conformation. As the strength of the interaction increases, the rings tend to get distorted, thus introducing a larger angular strain. Consequently, the distribution broadens, and once the network loses crystallinity, it is characterized by the emergence of a second peak at around -0.35. Therefore, even if rings with six members are present for all phases, structures in an arrested phase retain a completely different conformation owing to the random arrangement of the building blocks. The differences between the six-membered rings for the two analyzed phases are clearly visible from the simulation snapshots reported in Figs. 8(c) and 8(d) for a perfect diamond crystal grain and in Figs. 8(e) and 8(f) for a disordered gel-like configuration.

To further characterize the structural changes occurring across phases, we calculate the fractal dimension d_f of the gel-like structures, making use of the box counting algorithm.^{52,53} To this aim, after having identified the largest cluster, we subdivide the simulation box into cells of varying size λ and we count the number of cells N_c that contains at least one colloidal molecule. The fractal dimension is then obtained from

$$\log N_c(\lambda) = -d_f \log \lambda. \tag{7}$$



FIG. 8. Structural characterization of the diamond crystal and the percolating gel structures. (a) Fraction of six-membered rings $N_{y=6}/N$ as a function of simulation time t/τ for a system consisting of tetrahedral colloidal molecules with a core-to-lobe size ratio s = 1.24 and depletant-to-lobe size ratio q = 0.12 at a colloid number density $\rho\sigma_A^3 = 0.06$ for varying interaction strength βU as labeled [gray dashed line in Fig. 5(c)]. (b) Probability distribution of the angular strain $P(\xi)$ of rings consisting of six members for a crystal grain of cubic diamond and for a disordered gel configuration. (c) and (d) Typical simulation configurations of a diamond structure in which two different perspectives of six-membered rings are shown. Light blue lines highlight the chair-like conformation of the ring. (e) and (f) Typical simulation configurations of six-membered rings to a gel-like structure. The chair-like conformation and the corresponding internal angle distributions are no longer retained in this structure.

By fitting Eq. (7) in two different regimes, for large and small λ , it is possible to obtain information about the system at different length scales, corresponding to the internal structure and the mesoscopic scale.⁴⁹ Here, we discriminate between the two regimes by taking a crossover value $\lambda = 8\sigma_A$. An example of the fitting procedure and a schematic representation of the box counting method for the two λ -regimes are reported in Fig. S4. For a more reliable estimate of this quantity, the fitting is performed on simulations consisting of $N = 10\ 800$ colloidal molecules.

The fractal dimension for the two different length scales is reported in Fig. 9 for a system of colloidal molecules with a coreto-lobe size ratio s = 1.24 at different depletant-to-lobe size ratios q as a function of the interaction strength βU . For the smallest interaction strengths analyzed, d_f takes similar values at large length scales, always below 2.6 for all q. Globally, this indicates a compact structure, which, therefore, does not extend throughout the box, leaving large portions of empty space, as expected for a grain similar to the one shown in Fig. 6(b). At the same time, for small length scales, d_f takes the highest values at low interaction strengths. This indicates the tendency of local structures to have a conformation with a large homogeneity of the system, owing to the still large amount of diamond crystal that is present. Moving to $\beta U > 2$, the formation of percolating and disordered structures prevails and the trend of the fractal dimension reflects this phenomenon. In fact, on large scales, d_f tends to approach the highest value, suggesting

that globally the structure occupies the whole box. This picture is fully consistent with that depicted in Sec. III C for describing the branched and porous structure that comes along with the percolating gel network. At small length scales, the local disorder and the gradual decrease in the amount of crystal lower the fractal dimension and set it close to 2.

E. Kinetic phase diagram as a function of colloid density and interaction strength

We now explore in detail the kinetic phase diagram for a system of tetrahedral colloidal molecules as a function of colloid number density $\rho \sigma_A^3$ and interaction strength βU . To do so, we select a core-to-lobe size ratio *s* and a depletant size *q* for which we observe the formation of crystal grains of cubic diamond at low densities. In particular, we run simulations for *s* = 1.24 and *q* = 0.12 and vary the depletant reservoir packing fraction η_d^r and the colloid density $\rho \sigma_A^3$, respectively. With this approach, we range from a dilute state to a highly packed system. We present the kinetic phase diagram for q = 0.12 in Fig. 10 and for q = 0.25 in Fig. S5. The color code in the phase diagram indicates the number fraction N_D/N of particles in a cubic diamond environment, whose estimate is calculated based on the correlation parameter as before.

The structures that are identified are consistent with those observed in Fig. 5 at low densities. Representative simulation



FIG. 9. Fractal dimension d_f as a function of the interaction strength βU for different values of the depletant-to-lobe size ratio $q = \sigma_d/\sigma_A$ as labeled. Data are shown for a system of $N = 10\,800$ particles where the colloidal molecules have a core-to-lobe size ratio $s = \sigma_B/\sigma_A = 1.24$, at colloid density $\rho\sigma_A^3 = 0.06$. Closed symbols relate to the fractal dimension d_f at short length scales, while open symbols are for large length scales.

configurations of high-density structures are displayed in Fig. S6. Formation of crystalline cubic diamond is observed for a wide range of packing fractions of colloidal molecules, varying from the low density $\rho\sigma_A^3 = 0.06$ analyzed in Secs. III A, III C, and, III D up to a colloid density of $\rho\sigma_A^3 \approx 0.35$, corresponding to a colloid packing fraction range of $0.05 \leq \eta_c \leq 0.6$, for weak depletion attractions. This range is consistent with that found experimentally for tetrahedral colloidal molecules.³⁰ Instead, in comparison to simple tetrahedral patchy particles,¹¹ the range in which colloidal diamond is found is almost double in terms of packing fractions. In this sense, a key role is played by the structure of the particles. While in the



FIG. 10. Kinetic phase diagram for a system of DNA-functionalized tetrahedral colloidal molecules with a core-to-lobe size ratio $s = \sigma_A/\sigma_B = 1.24$ and a depletant-to-lobe size ratio $q = \sigma_d/\sigma_A = 0.12$ as a function of interaction strength βU (left axis) or depletant reservoir packing fraction η_d^r (right axis) and colloid number density $\rho \sigma_A^3$ (lower axis) or colloid packing fraction η_c (upper axis). The color bar on the right indicates the fraction of particles in a cubic diamond environment N_D/N .

case of tetrahedral colloidal molecules conformations not involving staggered bonds are actually disfavored, patchy particles could stabilize different crystal structures, such as body-centered cubic (bcc) and face-centered cubic (fcc) phases, at similar or higher packing fractions, respectively. For the tetrahedral colloidal molecules, such phases are not observed at any concentration. In terms of the strength of the interaction potential, this remains rather narrow. Only for low colloid densities, crystalline grains of diamond are found for relatively high interaction strengths $\beta U \approx 2.5$. At higher colloid densities, fully crystalline diamond structures are only found for lower βU .

The central region of the phase diagram is characterized by a lower number fraction N_D/N of colloidal diamond. In this region, the conformation of the crystalline diamond become more gel-like. For $\beta U \approx 1.8$, both ordered and disordered states coexist. By further increasing the interaction strength, a fully disordered structure emerges as expected. This change is also reflected in the diffraction pattern shown in Fig. S7, as compared to that of crystalline diamond. For high colloid densities $\rho \sigma_A^3$ and sufficiently high βU , the system is mostly in an arrested glassy state. Under these conditions, the depletion attractions are so strong that the system becomes arrested due to an attractive glass transition. The transition to this state finds evidence both in the diffraction patterns and in the mean squared displacement reported in Fig. S7. Accordingly, the fraction of colloidal molecules in a diamond environment found in this region is essentially negligible. Finally, we note that by changing the size of the central particle or the size of the depletants, the phase diagram does not present relevant changes at a qualitative level. Only some minor variations are observed in the range where the different phases are found.

IV. CONCLUSIONS

The self-assembly of cubic diamond is still an elusive process, which typically involves the use of anisotropic particles and directional interactions. Here, we explored in detail the self-assembly behavior of a model of tetrahedral colloidal molecules based on a recent experimental realization that was found to nucleate exclusively into cubic diamond.³⁰

For this purpose, we employed in our simulations a realistic set of interactions, including depletion between the monomers at the vertices of the tetrahedron and strong attractive interactions between the central core particles due to the presence of DNA. We found that the latter plays an important role in the formation of crystalline diamond. In particular, as compared to building blocks where the core is not functionalized, crystalline phases can be nucleated for a wider set of parameters by modifying the characteristics of the depletants. In the experiments of Ref. 30, the depletion interaction arises due to the presence of Pluronic F-127 micelles and a small amount of DNA. Our simulations suggest that any attractive interactions, e.g., other types of depletants, such as polystyrene⁴⁶ or critical Casimir interactions,⁵⁴ should also yield cubic diamond. By changing the concentration or the size of the depletants, the morphologies of the self-assembled structures can be tuned from an isotropic fluid phase via a colloidal crystal to a gel-like structure. From an experimental point of view, one could envision that the characteristics of the different structures may be altered in situ by means of microgel particles made of a responsive polymer, which

act as size-tunable depletants.^{37,55–57} In this way, one could explore a range of the depletant-to-lobe size ratio q that is comparable to the swelling ratio of the microgels, whose size typically varies by a factor of two by appropriately adjusting the temperature or the pH of the solution.

However, it should be emphasized that the formation of cubic diamond crystalline structures, which could find use in photonic crystals, remains limited to a relatively small range of interaction strengths, which is further restricted as the colloid density increases. Therefore, to avoid the formation of disordered gel structures and arrested states, it is essential to have a precise control on the interaction potentials and the thermodynamic state. We found, indeed, that a small deviation from the optimal conditions for nucleation and crystallization leads, at both low and intermediate colloid densities, to the formation of percolating structures with different degrees of crystallinity. This is consistent with earlier observations for a system of colloidal spheres that interact with short-range depletion interactions, where a subtle interplay is found between crystallization, gelation, and vitrification.^{43,46} The structural analysis we carried out for these structures, especially for $\beta U \gtrsim 3$, reveals a structure that percolates throughout the entire box. In addition, the loss of crystallinity at high interaction strengths βU is accompanied by an arrangement of colloidal molecules where the typical six-membered rings of the crystalline cubic diamond are distorted. At high βU , the attractive interactions due to the presence of the DNA at the surface of the core particles are no longer able to stabilize crystalline conformations and interactions occur mainly through the lobes.

In conclusion, this study elucidates under which conditions the formation of cubic diamond from a system of tetrahedral clusters is favored. Our results may find use in experimental and application studies where the formation of structures with photonic properties is required. Their assembly still remains a highly challenging task, and we believe that much work still has to be carried out. Even for the system explored in this paper, where crystalline cubic diamond can be assembled, a photonic bandgap opens up only for the inverse lattice. We hope that our results inspire future experiments in this direction or others in which alternative assembly routes are considered. In this regard, depletion interactions can perhaps be exploited to a greater extent.

SUPPLEMENTARY MATERIAL

See the supplementary material for further structural characterization of the phases and cluster formation, and for the kinetic phase diagrams of tetrahedral colloidal molecules without DNA functionalization and of systems of tetrahedral particles with depletant-to-lobe size ratio q = 0.25.

ACKNOWLEDGMENTS

The authors thank David J. Pine for valuable discussions. The authors acknowledge funding from the European Research Council (ERC) under European Union's Horizon 2020 Research and Innovation Program (Grant Agreement No. ERC-2019-ADG 884902, SoftML).

AUTHOR DECLARATIONS

Conflict of Interest

The authors have no conflicts to disclose.

Author Contributions

Susana Marín-Aguilar: Conceptualization (equal); Data curation (equal); Formal analysis (equal); Investigation (equal); Methodology (equal); Software (equal); Validation (equal); Visualization (equal); Writing – original draft (equal); Writing – review & editing (equal). Fabrizio Camerin: Conceptualization (equal); Data curation (equal); Formal analysis (equal); Investigation (equal); Methodology (equal); Software (equal); Validation (equal); Visualization (equal); Writing – original draft (equal); Writing – review & editing (equal); Writing – original draft (equal); Writing – review & editing (equal). Marjolein Dijkstra: Conceptualization (equal); Funding acquisition (lead); Project administration (lead); Resources (lead); Supervision (lead); Writing – original draft (equal); Writing – review & editing (equal).

DATA AVAILABILITY

The data that support the findings of this study are available from the corresponding author upon reasonable request.

REFERENCES

- ¹S. Sacanna and D. J. Pine, Curr. Opin. Colloid Interface Sci. 16, 96 (2011).
- ² M. Liu, X. Zheng, V. Grebe, D. J. Pine, and M. Weck, Nat. Mater. 19, 1354 (2020).
 ³ W. Li, H. Palis, R. Mérindol, J. Majimel, S. Ravaine, and E. Duguet, Chem. Soc.
- Rev. 49, 1955 (2020).
- ⁴V. N. Manoharan, Science **349**, 1253751 (2015).
- ⁵F. Li, D. P. Josephson, and A. Stein, Angew. Chem., Int. Ed. **50**, 360 (2011).
- ⁶J. Zhang, Z. Sun, and B. Yang, Curr. Opin. Colloid Interface Sci. 14, 103 (2009).
- ⁷É. Ducrot, M. He, G.-R. Yi, and D. J. Pine, Nat. Mater. 16, 652 (2017).
- ⁸M. Maldovan and E. L. Thomas, Nat. Mater. 3, 593 (2004).
- ⁹W. H. Brown, T. Poon, and T. Poon, *Introduction to Organic Chemistry* (John Wiley & Sons Hoboken, NJ, 2014), Vol. 7.
- ¹⁰E. Bianchi, R. Blaak, and C. N. Likos, Phys. Chem. Chem. Phys. 13, 6397 (2011).
- ¹¹F. Romano, E. Sanz, and F. Sciortino, J. Chem. Phys. **132**, 184501 (2010).
- ¹²E. G. Noya, C. Vega, J. P. K. Doye, and A. A. Louis, J. Chem. Phys. **132**, 234511 (2010).
- ¹³F. Romano, E. Sanz, and F. Sciortino, J. Chem. Phys. **134**, 174502 (2011).
- ¹⁴F. Leoni and J. Russo, Phys. Rev. X **11**, 031006 (2021).
- ¹⁵G. Doppelbauer, E. G. Noya, E. Bianchi, and G. Kahl, J. Phys.: Condens. Matter 24, 284124 (2012).
- ¹⁶E. G. Noya, I. Zubieta, D. J. Pine, and F. Sciortino, J. Chem. Phys. **151**, 094502 (2019).
- ¹⁷F. Romano, J. Russo, L. Kroc, and P. Šulc, Phys. Rev. Lett. **125**, 118003 (2020).
- ¹⁸Y. Ma, J. C. Aulicino, and A. L. Ferguson, J. Phys. Chem. B **125**, 2398 (2021).
- ¹⁹Y. Ma and A. L. Ferguson, Soft Matter 15, 8808 (2019).
- ²⁰N. Patra and A. V. Tkachenko, Phys. Rev. E **98**, 032611 (2018).

²²Y. Tian, J. R. Lhermitte, L. Bai, T. Vo, H. L. Xin, H. Li, R. Li, M. Fukuto, K. G. Yager, J. S. Kahn *et al.*, Nat. Mater. **19**, 789 (2020).

²⁴D. Morphew, J. Shaw, C. Avins, and D. Chakrabarti, ACS Nano 12, 2355 (2018).

²¹L. Rovigatti, J. Russo, F. Romano, M. Matthies, L. Kroc, and P. Šulc, "A simple solution to the problem of self-assembling cubic diamond crystals," arXiv:2205.10680 (2022).

²³ W. Liu, M. Tagawa, H. L. Xin, T. Wang, H. Emamy, H. Li, K. G. Yager, F. W. Starr, A. V. Tkachenko, and O. Gang, <u>Science</u> 351, 582 (2016).

²⁵ A. Neophytou, D. Chakrabarti, and F. Sciortino, Proc. Natl. Acad. Sci. U. S. A. 118 (2021).

²⁶A. Neophytou, V. N. Manoharan, and D. Chakrabarti, ACS Nano 15, 2668 (2021).

²⁷ A. B. Rao, J. Shaw, A. Neophytou, D. Morphew, F. Sciortino, R. L. Johnston, and D. Chakrabarti, ACS Nano 14, 5348 (2020).

²⁸P. F. Damasceno, M. Engel, and S. C. Glotzer, Acs Nano 6, 609 (2012).

²⁹Y. Zhou, R. K. Cersonsky, and S. C. Glotzer, Soft Matter 18, 304 (2022).

³⁰M. He, J. P. Gales, É. Ducrot, Z. Gong, G.-R. Yi, S. Sacanna, and D. J. Pine, Nature **585**, 524 (2020).

³¹Z. Gong, T. Hueckel, G.-R. Yi, and S. Sacanna, Nature 550, 234 (2017).

³²K. Miyazaki, K. S. Schweizer, D. Thirumalai, R. Tuinier, and E. Zaccarelli, "The Asakura-Oosawa theory: Entropic forces in physics, biology, and soft matter," J. Chem. Phys. **156**, 080401 (2022).

³³E. Zaccarelli, J. Phys.: Condens. Matter **19**, 323101 (2007).

³⁴J. Ruiz-Franco and E. Zaccarelli, Annu. Rev. Condens. Matter Phys. **12**, 51 (2021).

³⁵C. Patrick Royall, S. R. Williams, T. Ohtsuka, and H. Tanaka, Nat. Mater. 7, 556 (2008).

³⁶S. Kumar, M.-J. Lee, V. Aswal, and S.-M. Choi, Phys. Rev. E **87**, 042315 (2013).

³⁷L. Rossi, S. Sacanna, W. T. M. Irvine, P. M. Chaikin, D. J. Pine, and A. P. Philipse, Soft Matter 7, 4139 (2011).

³⁸D. J. Kraft, R. Ni, F. Smallenburg, M. Hermes, K. Yoon, D. A. Weitz, A. van Blaaderen, J. Groenewold, M. Dijkstra, and W. K. Kegel, Proc. Natl. Acad. Sci. U. S. A. **109**, 10787 (2012).

³⁹S. Asakura and F. Oosawa, J. Polym. Sci. 33, 183 (1958).

⁴⁰A. P. Thompson, H. M. Aktulga, R. Berger, D. S. Bolintineanu, W. M. Brown, P. S. Crozier, P. J. in't Veld, A. Kohlmeyer, S. G. Moore, T. D. Nguyen *et al.*, Comput. Phys. Commun. **271**, 108171 (2022).

⁴¹ P. J. Steinhardt, D. R. Nelson, and M. Ronchetti, Phys. Rev. B 28, 784 (1983).

⁴² A. H. Nguyen and V. Molinero, J. Phys. Chem. B **119**, 9369 (2015).

⁴³A. Fortini, E. Sanz, and M. Dijkstra, Phys. Rev. E 78, 041402 (2008).

⁴⁴P. J. Lu, E. Zaccarelli, F. Ciulla, A. B. Schofield, F. Sciortino, and D. A. Weitz, Nature **453**, 499 (2008).

⁴⁵F. Soto-Bustamante, N. E. Valadez-Pérez, Y. Liu, R. Castañeda-Priego, and M. Laurati, J. Colloid Interface Sci. 618, 442 (2022).

⁴⁶E. Zaccarelli, P. J. Lu, F. Ciulla, D. A. Waitz, and F. Sciortino, J. Phys.: Condens. Matter 20, 494242 (2008).

⁴⁷A. Stukowski, Jom 66, 399 (2014).

⁴⁸G. M. Coli, R. van Damme, C. P. Royall, and M. Dijkstra, "Crystal polymorph selection mechanism of hard spheres hidden in the fluid," arXiv:2108.07583 (2021).

49 S. Griffiths, F. Turci, and C. P. Royall, J. Chem. Phys. 146, 014905 (2017).

⁵⁰S. Marín-Aguilar, H. H. Wensink, G. Foffi, and F. Smallenburg, Phys. Rev. Lett. 124, 208005 (2020).

⁵¹ K. B. Wiberg, Angew. Chem., Int. Ed. Engl. 25, 312 (1986).

⁵²J. J. Gagnepain and C. Roques-Carmes, Wear **109**, 119 (1986).

⁵³J. Ruiz-Franco, F. Camerin, N. Gnan, and E. Zaccarelli, Phys. Rev. Mater. 4, 045601 (2020).

⁵⁴C. Hertlein, L. Helden, A. Gambassi, S. Dietrich, and C. Bechinger, Nature 451, 172 (2008).

⁵⁵L. Rossi, V. Soni, D. J. Ashton, D. J. Pine, A. P. Philipse, P. M. Chaikin, M. Dijkstra, S. Sacanna, and W. T. M. Irvine, Proc. Natl. Acad. Sci. U. S. A. 112, 5286 (2015).

⁵⁶X. Xing, L. Hua, and T. Ngai, Curr. Opin. Colloid Interface Sci. 20, 54 (2015).

⁵⁷M. J. Bergman, N. Gnan, M. Obiols-Rabasa, J.-M. Meijer, L. Rovigatti, E. Zaccarelli, and P. Schurtenberger, Nat. Commun. 9, 5039 (2018).